

Original Article

Biosynthesis, Characterization and Antibacterial Properties of ZnO Nanoparticles of Cold Tolerant *Microbacterium* sp.

Bashir Ahmad Aseem¹, Mohammad Arif Ahsas²

^{1,2}Department of Biology, Ghor Institute of Higher Education, Ghor Province, Afghanistan.

Received: 01 October 2022

Revised: 01 November 2022

Accepted: 12 November 2022

Published: 30 November 2022

Abstract - Nanotechnology has attracted great interest recently due to its unexpected impact on many areas of science and life, especially in biology and biomedicine. Nanoparticles, due to their unique physical, chemical, optical, electrical, and magnetic properties, have increased interest in their synthesis. They have been synthesized by various physical and chemical processes, but most of these methods require a vast amount of energy or cannot avoid the formation of toxic byproducts in their synthesis process. Therefore, there is an urgent need to develop green processes for nanoparticle synthesis. Such as the biological synthesis of nanoparticles by bacteria has been considered. In this study, zinc oxide nanoparticles were biosynthesized by using microbial culture supernatant from the cold-tolerant strain of *Microbacterium* sp. OSNP13. The Biosynthesized nanoparticles were characterized by UV-Vis, DLS and XRD analysis. The results indicated that the average size of zinc oxide nanoparticles was 59.16 nm. The antibacterial activity of the produced nanoparticles was then evaluated. The MIC of zinc oxide nanoparticles for *E. coli* and *S. aureus* was also calculated to be 500 µg/ml. The zinc oxide nanoparticles produced in this study have shown good antimicrobial properties and can be suitable candidates for use as antimicrobial agents.

Keywords - Antibacterial activity, Cold-tolerant microbacterium sp, Minimum bactericidal concentration, Minimum inhibitory concentration, Zinc oxide nanoparticles.

1. Introduction

Nanotechnology is a technology field in which humans can design different types of compounds, alloys, devices and tools and, in general, various systems and structures or factors in atomic and molecular scale and nanometer dimensions and bring them to the manufacturing stage. Antibiotics are widely used in health care. As a result, pathogens are becoming antibiotic-resistant microbes and becoming serious diseases for human health. In the last decades, scientists all over the world have been looking for new antimicrobial agents with increased ability. [1-3] Several nanomaterials have been developed to meet the ever-increasing demand for more effective antibacterial agents. However, many antimicrobial nanomaterials reported so far are associated with concerns about toxicity, environmental pollution, biological incompatibility and complex synthesis methods. [4] As a result, there is still a challenge to produce efficient, new and environmentally friendly antibacterial nanomaterials. Zinc oxide is a crystalline semiconductor oxide with a direct energy gap of 3.37 eV. The important crystalline structure of zinc oxide is its wurtzite type. Zinc oxide is one of the primary metal nanoparticles due to its unique properties and high energy gap, which has various applications in industry and environmental sciences. The immunity of Zinc oxide and its compatibility with human skin makes it a suitable additive for textiles and surfaces that

come into contact with the human body. [5-8] Zinc oxide nanoparticles show antimicrobial effects on Gram-positive and Gram-negative bacteria and spores resistant to high and low temperatures. [9-11]

The antimicrobial activities of Zinc oxide nanoparticles have been improved compared to micro particles due to the increase in the surface of nanoparticles, so the smaller the size of the particles, the greater the antimicrobial properties. [12] In general, Zinc oxide reduces the ability of bacteria; However, the mechanism of its antimicrobial activity is not well known yet. It suggests that the main factor of antimicrobial activities can be hydrogen peroxide production. The accumulation of particles on the surface of bacteria due to electrostatic force can be another mechanism of the antimicrobial effect of Zinc oxide nanoparticles. [31] However, interacting types of the produced oxygen on the surface of the particles, release of Zinc ions, disturbance in membrane and membrane processes, as well as the internal nanoparticles can be the possible causes of cell damage. [14]

Considering the efficient metal resistance mechanisms and the high potential of Psychotropic microorganisms in the synthesis of nanoparticles and the very few studies that have been done regarding the synthesis of metal nanoparticles with these microorganisms, therefore, in the present research,



the ability of new strains of cold-resistant bacteria isolated from the Zagros highlands located in Lorestan province of Iran and some strains of *Streptomyces* isolated from the Sea of Oman to synthesize and determine the structure of Zinc oxide nanoparticles and its inherent properties as antibacterial agents have been studied.

2. Review of Literature

In 2012, Jayaseelan, Abdul Rahuman, Vishnu Kirthi, Marimuthu, Santhoshkumar, Bagavan, Gaurav, Karthik and Bhaskara Rao produced zinc oxide nanoparticles with a spherical structure and an average size of 57 nm by *Aeromonas hydrophila* bacteria. Moreover, the antibacterial properties of nanoparticles on *Pseudomonas aeruginosa* and *Aspergillus flavus* were evaluated by the agar well diffusion method. The growth inhibition halo diameter was reported to be 22 and 19 mm for these two pathogens, respectively. [15]

In 2014, Kundu, Hazra, Chatterjee, Chaudhari and Mishra produced ZnO nanoparticles by *Rhodococcus pyridinivorans* NT2 bacteria. The nanoparticles produced an average size of 100 to 120 nm and showed appropriate antimicrobial and anticancer properties against *Staphylococcus epidermidis* NCIM2943 and HT-29 cell lines, respectively. In this research, the precursor used for the production of nanoparticles was copper sulfate. [16]

In 2018, Sharmila, Muthukumar, Santhiya, Pradeep, Manoj Kumar, Suriyanarayanan and Thirumarimurugan produced zinc oxide nanoparticles from *Bauhinia tomentosa* leaf extract. The produced nanoparticles had a hexagonal structure, and the average particle size was 22 to 94 nm. The produced nanoparticles also showed an appropriate antimicrobial properties against *P. aeruginosa* and *E.coli* Gram-negative Bacteria. [17]

The production of zinc oxide nanoparticles by the liquid extract of the stem of the *Albizia lebbek* plant was carried out by Umar, Kavaz and Rizaner in 2019. The average size of the produced nanoparticles was 66.25 nm. The produced nanoparticles had anticancer properties on MDA-MB 231 and MCF-7 cell lines. [18]

3. Materials and Methods

3.1. The Investigated Strains

In this research, the 44 cold-resistant isolated strains from Zagros highlands located in Lorestan province and some *Streptomyces* strains from the Oman Sea were purified. Then, their ability to produce Zinc oxide nanoparticles was investigated.

3.2. The Determination of the Maximum Tolerance Concentration (MTC)

First, solid culture medium (TSB) 200ml with different concentrations (2.5, 5, 10, 25 and 50 Mm/l) of $ZnSO_4 \cdot 4H_2O$,

$Zn(NO_3)_2 \cdot 5H_2O$ salts were prepared in separate jars, then the contents of each of the jars were transferred into sterilized microbial plates and were placed at 30°C for 24 hours. Then, all the plates were divided into different parts and the plates without salt (Zinc) were considered the control for bacteria's growth. Then, 5 µL of the suspension of the studied strains (24-hour culture) with a 0.5 McFarland turbidity inoculates on each of the plates. All the plates were placed in a greenhouse at 20°C and 30°C for 48 hours. A high concentration of metal in which bacteria cannot grow was introduced as MTC, and in this way, resistant and efficient strains were identified in reducing zinc cations. [19]

3.3. Synthesis, Characterization of Zinc Oxide Nanoparticles and Molecular Identification of the Producing Strain

The selected strains were inoculated in 400 ml of TSB liquid culture medium and were kept in a greenhouse for 48 hours in a shaker incubator at 20 °C at 150 rpm. After the growth and proliferation of cells, the resulting supernatant was separated by centrifugation at a speed of 1000 rpm for 15 minutes. The resulting supernatant was added with nitrate and sulfate salts with a concentration of 0.01 Molar in a ratio of 1:1. All the samples were placed in an autoclave with a temperature of 121°C for 15 minutes. After 24 hours of incubation at room temperature, the produced nanoparticles were separated by centrifugation, and after washing three times with deionized water and ethanol, they were dried at a temperature of 80°C. In order to remove the biological agents on the surface of the nanoparticles, the produced nanoparticles were placed in an oven at 470°C for 4 hours. [20] Then, the strain with the highest amount of sediment formation and color change of the supernatant was selected for purification and characterization of the synthesized zinc oxide nanoparticles. The purified nanoparticles were analyzed to measure the optical absorption by UV-vis spectrophotometer in the 200-400 nm range. Furthermore, some of the obtained sediment was used for X-ray diffraction (XRD) and dynamic light scattering (DLS) analysis. Molecular identification of the selected strain was made by amplifying and sequencing the 16srRNA gene.

3.4. Measuring the Antibacterial Activity of Nanoparticles

To study the antibacterial properties of zinc oxide nanoparticles, stock of 2000 µg/ml of the nanoparticles was dispersed in ammonium citrate at a ratio of 2:1 and 40% glycerol. *E. coli* and *S. aureus* bacteria were inoculated in MHB sterile medium and kept in a greenhouse at 37 °C for 18 hours. Moreover, finally, by using physiological serum (0.9% sodium chloride), the turbidity of bacteria was adjusted in half McFarland (absorbance 0.08-0.13 at 630 nm wavelength), which in this case, the number of bacteria is equal to 1.5×10^8 CFU/ml. The antibacterial activity of nanoparticles in different concentrations (4000 to 125 micrograms/ml) was used using the micro-dilution method. [21].

4. Results and Discussion

The resistance level of 44 cold-resistant and *Streptomyces* strains to two salts, zinc sulfate and zinc nitrate, was evaluated at concentrations (2.5, 5, 10, 25 and 50 mM). The results showed that all strains could resist at more than 5 mM concentrations. According to the initial culture results, two cold-resistant strains and two *Streptomyces* strains were selected and also considering the results of the MTC test, the resistance of these strains to the zinc sulfate salt was more than that of the zinc nitrate. Therefore, concentrations of 10 mmol/L zinc sulfate were used to produce nanoparticles. In the following, *Streptomyces* strains were excluded from further analysis due to their slow growth. Of these, the OSNP13 strain with the highest amount of sediment formation and color change of the supernatant, along with heating in the autoclave, was selected for the purification and analysis of zinc oxide nanoparticles (figure 1).




Fig. 1 Production of oxide nanoparticles using the microbial culture supernatant method with autoclave heat. A and B, respectively, the supernatant of the OSNP13 strain, the supernatant after adding zinc sulfate salt and placing it in the autoclave.

In this method, the production of nanoparticles is in autoclave conditions or high pressure and temperature, the metal ions in the used salts are mostly in contact with the functional groups and secondary metabolites in the microbial culture supernatant, and the reaction of producing nanoparticles or nucleation is done at a faster rate. Many studies have mentioned that NADH-dependent enzymes have an important role in electron transfers during the biological production of nanoparticles. Therefore, there is no report about the production of zinc oxide nanoparticles by cold-resistant strains with this method. Ghanbari, Vaghari, Sayyar, Adibpour & Jafarizade 2017, succeeded in producing silver nanoparticles by using *Aspergillus fumigatus* supernatant in autoclave conditions. [20] The results of UV-vis spectroscopy in Figure 2 show a distinct peak between 200 and 400 nm with maximum absorption at 269 nm, which indicates the presence of zinc oxide nanoparticles in the interaction solution and is caused by the superficial Plasmon resonance characteristic of these nanoparticles.




Fig. 2 Uv-vis spectroscopy diagram for zinc oxide nanoparticles

The observed peak for zinc oxide nanoparticles correspondent with the studies of Fooladsaz, Negahdary, Rahimi, Habibi-Tamijani, Parsania & Akbari-dastjerdi 2012 and Patil & Taranath 2016. [22,23] The nanoparticle size distribution diagram showed that the synthesized zinc oxide nanoparticles by *Microbacterium* sp. OSNP13 has an average size of 59.16 nm. As shown in Figure 3, the size distribution curve of the nanoparticles is almost bell-shaped, which indicates the distribution of the uniform proportion of the synthesized zinc oxide nanoparticles. The polydispersity index (PDI) of nanoparticles was recorded as 0.19, which indicates the high uniformity of the colloidal solution of nanoparticles synthesized in this study (figure 3). Based on reliable references, it has been reported that a uniform colloid sample of nanoparticles in which the monodispersity of the particles is high has a PDI between 0.01 to 0.7. Non-uniform and polydisperse samples have a PDI higher than 0.7 to 1, which is inappropriate. [32]

In Ghorbani, Mehr, Pazoki & Rahmani's study in 2015, according to the results of the DLS technique, the average size of oxide nanoparticles produced by the co-precipitation method was reported to be 30 nm. [25] The difference in the average size of nanoparticles with the present study is due to the different method of nanoparticles production in these two studies.

In order to determine the network type and prove the crystalline structure of the zinc oxide nanoparticles, XRD analysis was used at 2θ angle and scanning range from 20 to 80 degrees which has specific peaks at the levels of 100, 002, 101, 102, 110, 103, 200, 112, 201 and 004 that shows the monoclinic structure of zinc oxide nanoparticles and is entirely consistent with standard pattern (JCPDS File) 0002-043 (figure 4). [26].




Fig. 3 The size distribution pattern of the synthesized zinc oxide nanoparticles.




Fig. 4 X-ray refraction analysis of zinc oxide nanoparticles.

The observed pattern for zinc oxide nanoparticles in the Raoufi study in 2013 and Anvekar, Chari & Kadam in 2017 is entirely consistent with the pattern observed in this study. [27,28] According to the calculations based on the Debye-Scherrer equation, the average size of the nanocrystals was calculated to be 19.25 nm for zinc oxide nanoparticles at an angle of 36.21 with the 101 crystal plane. The results of this section are consistent with the results of DLS analysis and indicate the smaller size of the produced zinc oxide nanoparticles.

Regarding the molecular identification of the strain that produces zinc oxide nanoparticles, after determining the sequence of the 16SrRNA gene, and matching the results with EZTaxon and NCBI databases, the strain of *Microbacterium* sp. OSNP13 belongs to the genus *Microbacterium* with 100% similarity. In the continuation of the antibacterial effect of ZnO nanoparticles produced by *Microbacterium* sp. SNP13 on Gram-negative *E. coli* and gram-positive *S. aureus* bacteria were investigated as indicators of gram-negative and gram-positive pathogens, respectively, in the concentrations range of 4000 to 125 µg/ml by broth microdilution method. (MIC) and (MBC)

values of zinc oxide nanoparticles for two bacteria, *E. coli* and *S. aureus*, were calculated as 500 and 1000 µg/ml, respectively (Table 1).

Table 1. MIC and MBC values of zinc oxide nanoparticles.

Nanoparticles	MIC(µg/ml)	MBC(µg/ml)	Bacteria
ZnO NPs	500	1000	<i>E. coli</i>
	500	1000	<i>S. aureus</i>

With the increase in concentrations of nanoparticles, a greater decrease is observed in the growth of bacteria compared to the control sample, and this increased inhibition depends on the concentration of nanoparticles. At concentrations lower than the MIC, nanoparticles inhibit the growth of part of the microbial population and are unable to inhibit the growth of the entire microbial population (Figure 5).




Fig. 5 The inhibition percentage of the growth of pathogenic bacteria in different concentrations of zinc oxide nanoparticles

The results showed that the lethal concentration of nanoparticles used in this research had the same effects on Gram-positive and Gram-negative bacteria (Figure 6).




Fig. 6 MBC test results for zinc oxide nanoparticles after 18 hours of greenhouse storage

In 2017 Şahin, Musevi & Aslani. reported the MIC value of zinc oxide nanoparticles produced in their studies on *E. coli* ATCC 25922 as 512 µg/ml. Which is higher than the values calculated for the nanoparticles of this research. [29]

In 2013, Siddique, Shah, Shahid & Yasmin reported the MIC values of zinc oxide nanoparticles for *E. coli* and *S. aureus* as 21 and 8 mM, respectively (each milli molar was equivalent to 72 micrograms/ml), compared to the results of this research, the produced nanoparticles have shown less antimicrobial properties. Of course, comparing the nanoparticles used in this research has shown a suitable inhibitory and lethal effect compared to previous studies. [30]

5. Conclusion

In this research, the ability of cold-resistant bacteria was used in the biosynthesis of oxide nanoparticles—the production of zinc oxide nanoparticles by the selected strain of *Microbacterium* sp.OSNP13 was evaluated using the microbial culture supernatant method and heating in

autoclave conditions. The structure and characteristics of the produced nanoparticles were characterized by using Uv-Vis, XRD and DLS analyses.

The characterization results have shown the accuracy of the production of these nanoparticles. According to the DLS analysis, the average size of the produced zinc oxide is 59.16 nm. Also, the polydispersity index (PDI) was calculated at 0.19 for zinc oxide nanoparticles at physiological pH, indicating these nanoparticles' relatively appropriate uniformity. The size of nanocrystals was also calculated using the Debye-Scherrer equation and 19.25 nm. The results are consistent with the results of DLS analysis and indicate the smaller size of the produced zinc oxide nanoparticles. Examining the antimicrobial effect of nanoparticles on *E. coli* and *S. aureus* bacteria showed that, in general, the produced nanoparticles have significant antibacterial properties that can be used as an antimicrobial agent in many different fields, including Medical equipment, antibacterial surfaces, etc.

6. References

- [1] W. Hu, C. Peng, W. Luo, M. Lv, X. Li, D. Li, Q. Huang and C. Fan, "Graphene-Based Antibacterial Paper," *ACS Nano*, vol. 4, no. 7, pp. 4317-4323, 2010. Crossref, <https://doi.org/10.1021/nn101097v>
- [2] Z. Li, F. Zhang, A. Meng, C. Xie, and J. Xing, "Zno/Ag Micro/Nanospheres with Enhanced Photocatalytic and Antibacterial Properties Synthesized by a Novel Continuous Synthesis Method," *RSC Advances*, vol. 5, no. 1, pp. 612-620, 2015. Crossref, <https://doi.org/10.1039/C4RA12319K>
- [3] C. Buzea, I. I. Pacheco, and K. Robbie, "Nanomaterials and Nanoparticles: Sources and Toxicity," *Biointerphases*, vol. 2, no. 4, MR17–MR71, 2007. Crossref, <https://doi.org/10.1116/1.2815690>
- [4] N. Musee, M. Thwala and N. Nota, "The Antibacterial Effects of Engineered Nanoparticles: Implication for Wastewater Treatment Plants," *Journal of Environmental Monitoring*, vol. 13, no. 5, pp. 1164-1183, 2011. Crossref, <https://doi.org/10.1039/C1EM10023H>
- [5] L. Qian, Z. Min, Z.-x. Fang and X.-h. Rong, "Effects of ZnO Nanoparticles and Microwave Heating on the Sterilization and Product Quality of Vacuum-Packing Caixin," *Journal of the Science of Food and Agriculture*, vol. 94, no. 12, pp. 2547-2554, 2014. Crossref, <https://doi.org/10.1002/jsfa.6594>
- [6] B. V. Ischenko, S. Polarz, D. Grote, V. Stavarache, K. Fink, and M. Driess, "Zinc Oxide Nanoparticles with Defects," *Advanced Functional Materials*, vol. 15, no. 12, pp. 1945-1954, 2005. Crossref, <https://doi.org/10.1002/adfm.200500087>
- [7] R. R. J. C. Tarafdar, "ZnO Nanoparticle Biosynthesis and Its Effect on Phosphorous-Mobilizing Enzyme Secretion and Gum Contents in Clusterbean (*Cyamopsis tetragonoloba* L.)," *Agricultural Research*, vol. 2, pp. 48-57, 2013. Crossref, <https://doi.org/10.1007/s40003-012-0049-z>
- [8] Y. Xie, Y. He, P. L. Irwin, T. Jin, and X. Shi, "Antibacterial Activity and Mechanism of Action of Zinc Oxide Nanoparticles against *Campylobacter* Jejuni," *Applied and Environmental Microbiology*, vol. 77, no. 7, pp. 2325-2331, 2011. Crossref, <https://doi.org/10.1128/AEM.02149-10>
- [9] A. Azam, A. S Ahmed, M. Oves, M. S Khan, S. S Habib and A. Memic, "Antimicrobial Activity of Metal Oxide Nanoparticles Against Gram-Positive and Gram-Negative Bacteria: A Comparative Study," *International Journal of Nanomedicine*, vol. 7, pp. 6003-6009, 2012. Crossref, [10.2147/IJN.S35347](https://doi.org/10.2147/IJN.S35347)
- [10] R. R. Vittal and J. B. Aswathanarayan, "Nanoparticles and their Potential Application as Antimicrobials," *Science Against Microbial Pathogens: Communicating Current Research and Technological Advances*, pp. 197-209, 2011.
- [11] Solmaz Maleki Dizaj, Farzaneh Lotfipour, Mohammad Barzegar-Jalali, Mohammad Hossein Zarrintan, Khosro Adibkia, "Antimicrobial Activity of the Metals and Metal Oxide Nanoparticles," *Materials Science and Engineering C*, vol. 44, pp. 278-284, 2014. Crossref, <https://doi.org/10.1016/j.msec.2014.08.031>
- [12] N. Padmavathy and R. Vijayaraghavan, "Enhanced Bioactivity of ZnO Nanoparticles — An Antimicrobial Study," *Science and Technology of Advanced Materials*, vol. 9, no. 3, 2008. Crossref, <https://doi.org/10.1088/1468-6996/9/3/035004>

- [13] S. Priyanka, A. Merline Sheela, "Comparing the Antibacterial Activity of Silver Nanoparticles Synthesized Using Garlic Extract and Celery Leaf Extract and Implementing in Domestic Point Use filters," *SSRG International Journal of Agriculture & Environmental Science*, vol. 4, no. 3, pp. 24-33, 2017. Crossref, <https://doi.org/10.14445/23942568/IJAES-V4I3P105>
- [14] M. J. Hajipour, K. M. Fromm, A. A. Ashkarran, D. J. De Aberasturi, I. R. De Larramendi, and T. Rojo, "Antibacterial Properties of Nanoparticles," *Trends Biotechnology*, 2012. Crossref, 10.1016/j.tibtech.2012.06.004
- [15] J. Chidambaram, A. Abdul Rahuman, V. Vishnu Kirthi, S. Marimuthu, T. Santhoshkumar, A. Bagavan, K. Gaurav, L. Karthik and KV Bhaskara Rao, "Novel Microbial Route to Synthesize ZnO Nanoparticles using Aeromonas Hydrophila and their Activity Against Pathogenic Bacteria and Fungi," *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, vol. 90, pp. 78-84, 2012. Crossref, <https://doi.org/10.1016/j.saa.2012.01.006>
- [16] D. Kundu, C. Hazra, A. Chatterjee, A. Chaudhari and S. Mishra, "Extracellular Biosynthesis of Zinc Oxide Nanoparticles Using Rhodococcus Pyridinivorans NT2: Multifunctional Textile Finishing, Biosafety Evaluation and in Vitro Drug Delivery in Colon Carcinoma," *Journal of Photochemistry and Photobiology B: Biology*, vol. 140, pp. 194-204, 2014. Crossref, <https://doi.org/10.1016/j.jphotobiol.2014.08.001>
- [17] G. S. C. Muthukumar, K. S. S. Santhiya, R. S. Pradeep, and N. M. Kumar, "Biosynthesis, Characterization, and Antibacterial Activity of Zinc Oxide Nanoparticles Derived from Bauhinia Tomentosa Leaf Extract," *Journal of Nanostructure in Chemistry*, vol. 8, no. 3, pp. 293-299, 2018. Crossref, <https://doi.org/10.1007/s40097-018-0271-8>
- [18] H. Umar, D. Kavaz and N. Rizaner, "Biosynthesis of Zinc Oxide Nanoparticles Using Albizia Lebbeck Stem Bark, and Evaluation of its Antimicrobial, Antioxidant, and Cytotoxic Activities on Human Breast Cancer Cell Lines," *International Journal of Nanomedicine*, vol. 14, pp. 87-100, 2018. Crossref, <https://doi.org/10.2147/IJN.S186888>
- [19] S. Shakya, B. Pradhan, L. Smith, J. Shrestha, and S. Tuladhar, "Isolation and Characterization of Aerobic Culturable Arsenic-Resistant Bacteria from Surfacewater and Groundwater of Rautahat District, Nepal," *Journal of Environmental Management*, vol. 95, pp. S250-S255, 2020. Crossref, <https://doi.org/10.1016/j.jenvman.2011.08.001>
- [20] Ghanbari, Sarah, Vaghari, Hamideh, Sayyar, Zahra, Adibpour, Mohammad and Jafarizadeh-Malmiri, Hoda, "Autoclave-Assisted Green Synthesis of Silver Nanoparticles Using A. Fumigatus Mycelia Extract and the Evaluation of their Physico-Chemical Properties and Antibacterial Activity," *Green Processing and Synthesis*, vol. 7, no. 3, pp. 217-224, 2018. Crossref, <https://doi.org/10.1515/gps-2017-0062>
- [21] J. M. Andrews, "Determination of Minimum Inhibitory Concentrations," *Journal of Antimicrobial Chemotherapy*, vol. 48, pp. 5-16, 2001. Crossref, https://doi.org/10.1093/jac/48.suppl_1.5
- [22] K. Fooladsaz, M. Negahdary, G. Rahimi, A. Habibi-Tamijani, S. Parsania, H. Akbari-dastjerdi, A. Sayad, A. Jamaledini, F. Salahi and A. Asadi, "Dopamine Determination with a Biosensor Based on Catalase and Modified Carbon Paste Electrode with Zinc Oxide Nanoparticles," *International Journal of Electrochemical Science*, vol. 7, pp. 9892-9908, 2012.
- [23] B. N. Patil and T. C. Taranath, "Limonia Acidissima L. Leaf Mediated Synthesis of Zinc Oxide Nanoparticles : A Potent Tool Against Mycobacterium Tuberculosis," *International Journal of Mycobacteriology*, vol. 5, no. 2, pp. 197-204, 2016. Crossref, <https://doi.org/10.1016/j.ijmyco.2016.03.004>
- [24] Muhammad Aziz Choudhary, Roquia Manan, Muhammad Aslam Mirza, Humaira Rashid Khan, Somia Qayyum and Zahoor Ahmed, "Biogenic Synthesis of Copper oxide and Zinc oxide Nanoparticles and their Application as Antifungal Agents," *SSRG International Journal of Material Science and Engineering*, vol. 4, no. 1, pp. 1-7, 2018. Crossref, <https://doi.org/10.14445/23948884/IJMSE-V4I1P101>
- [25] H. R. Ghorbani, F. P. Mehr, H. Pazoki, and B. M. Rahmani, "Synthesis of ZnO Nanoparticles by Precipitation Method," *Oriental Journal of Chemistry*, vol. 31, no. 2, pp. 9-11, 2015. Crossref, <http://dx.doi.org/10.13005/ojc/310281>
- [26] M. Shatnawi, A.M. Alsmadi, I. Bsoul, B. Salameh, M. Mathai, G. Alnawashi, Gasseem M. Alzoubi, F. Al-Dweri, M.S. Bawa'aneh, "Results in Physics Influence of Mn Doping on the Magnetic and Optical Properties of ZnO Nanocrystalline Particles," *Results in Physics*, vol. 6, pp. 1064-1071, 2016. Crossref, <https://doi.org/10.1016/j.rinp.2016.11.041>
- [27] D. Raoufi, "Synthesis and Microstructural Properties of ZnO Nanoparticles Prepared by Precipitation Method Synthesis and Microstructural Properties of ZnO Nanoparticles Prepared by Precipitation Method," *Renewable Energy*, vol. 50, pp. 932-937, 2013. Crossref, <https://doi.org/10.1016/j.renene.2012.08.076>
- [28] T. S. Avenkar, V. R. Chari and H. Kadam, "Green Synthesis of ZnO Nanoparticles, its Characterization and Application," *Material Science Research India*, vol. 14, no. 2, pp. 153-157, 2017. Crossref, <http://dx.doi.org/10.13005/msri/140211>
- [29] E. Sahin, S. J. Musevi and A. Aslani, "Antibacterial Activity Against Escherichia Coli and Characterization of ZnO and ZnO – Al₂O₃ Mixed Oxide Nanoparticles," *Arabian Journal of Chemistry*, vol. 10, pp. S230-S235, 2017. Crossref, <https://doi.org/10.1016/j.arabjc.2012.07.027Get>
- [30] S. Siddique, Z. H. Shah, S. Shahid, and F. Yasmin, "Preparation, Characterization and Antibacterial Activity of ZnO Nanoparticles on Broad Spectrum of Microorganisms," *Acta Chimica Slovenica*, vol. 60, no. 3, pp. 660-665, 2013.

- [31] L. Zhang, Y. Ding, M. Povey, and D. York, "ZnO Nanofluids – A Potential Antibacterial Agent," *Progress in Natural Science*, vol. 18, no. 8, pp. 939-944, 2008. Crossref, <https://doi.org/10.1016/j.pnsc.2008.01.026>
- [32] S. Honary, H. Barabadi, E. Gharaei-fathabad, and F. Naghibi, "Green Synthesis of Silver Nanoparticles Induced by the Fungus *Penicillium Citrinum*," *Tropical Journal of Pharmaceutical Research*, vol. 12, no. 1, pp. 7-11, 2013. Crossref, <https://doi.org/10.4314/tjpr.v12i1.2>